Translation.





PCT

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

(Chapter II of the Patent Cooperation Treaty)

(PCT Article 36 and Rule 70)

	(2 0 2 1 2 3 3 3 3				
Applicant's or agent's file reference F-1002	FOR FURTHER AC	CTION	See Form PCT/IPEA/416		
International application No. PCT/JP2003/010056	International filing date 07 August 2003		Priority date (day/month/year) 09 August 2002 (09.08.2002)		
International Patent Classification (IPC) or H01L 21/66					
Applicant	JSR CORP	ORATION			
This report is the international pre Authority under Article 35 and tra			s International Preliminary Examining 6.		
2. This REPORT consists of a total of	ofsheets,	, including this cover	sheet.		
3. This report is also accompanied by	ANNEXES, comprising	•			
a. (sent to the applicant a	nd to the International Bu	reau) a total of 3	sheets, as follows:		
and/or sheets co	sheets of the description, claims and/or drawings which have been amended and are the basis of this report and/or sheets containing rectifications authorized by this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions).				
beyond the disc	sheets which supersede earlier sheets, but which this Authority considers contain an amendment that goes beyond the disclosure in the international application as filed, as indicated in item 4 of Box No. I and the Supplemental Box.				
	indicated in the Suppler	ining a sequence listi	ype and number of electronic carrier(s)) ng and/or tables related thereto, in computer to Sequence Listing (see Section 802 of the		
4. This report contains indications re					
Box No. I Basis of the	report				
Box No. II Priority					
Box No. III Non-establi	shment of opinion with re	gard to novelty, inver	ntive step and industrial applicability		
Box No. IV Lack of uni	ty of invention				
l —	uments cited	such statement			
Box No. VII Certain defe	ects in the international ap	plication			
Box No. VIII Certain observations on the international application					
Date of submission of the demand		Date of completion	of this report		
06 February 2004 (06.02.2004)		15 July 2004 (15.07.2004)			
Name and mailing address of the IPEA/JP		Authorized officer			
Facsimile No.		Telephone No.			

Box N	o. I	Basis of the report	
1. Wit	h regard rwise ir	to the language, this report is based on the international application in the la	nguage in which it was filed, unless
	This whic	report is based on translations from the original language into the following his language of a translation furnished for the purpose of:	ng language,
		international search (under Rules 12.3 and 23.1(b))	
		publication of the international application (under Rule 12.4)	
		international preliminary examination (under Rules 55.2 and/or 55.3)	
i		•	
	are not	to the elements of the international application, this report is based on the receiving Office in response to an invitation under Article 14 are referrannexed to this report): atternational application as originally filed/furnished	(replacement sheets which have been red to in this report as "originally filed"
		scription:	
	pages	1-84	
	pages'		, as originally filed/furnished
	pages*	received by this Authority on	
	the cla		
	pages	2-3, 1114	
	pages*		, as originally filed/furnished
	pages*	1, 5-8, 10 received by this Authority on	gether with any statement) under Article 19
	pages*	received by this Authority on	08 July 2004 (08.07.2004)
\boxtimes	the dra	wings:	
	pages	1/12-12/12	
	pages*		, as originally filed/furnished
	pages*	received by this Authority on	
\Box	a seque	ence listing and/or any related table(s) - see Supplemental Box Relating to Se	
3. 🔀	The am	nendments have resulted in the cancellation of:	quence Listing.
	<u>M</u>	ne claims, Nos. 4, 9	
	L t	ne drawings, sheets/figs	
	L t	ne sequence listing (specify):	
	a:	ny table(s) related to sequence listing (specify):	
4. 🔲	This reproduced in the control of th	port has been established as if (some of) the amendments annexed to this resince they have been considered to go beyond the disclosure as filed, as 0.2(c)). The description, pages	eport and listed below had not been indicated in the Supplemental Box
* If item	4 applie	es, some or all of those sheets may be marked "superseded."	

V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement

Statement			
Novelty (N)	Claims	1-3, 5-8, 10-14	YES
	Claims		NO
Inventive step (IS)	Claims	1-3, 5-8, 10-14	YES
	Claims		NO
Industrial applicability (IA)	Claims	1-3, 5-8, 10-14	YES
	Claims		NO

2. Citations and explanations

Document 1: WO 02/47149 A1 (JSR Corp.) Document 2: JP 2002-203879 A (JSR Corp.)

None of the documents cited in the international search report discloses the inventions described in claims 1 to 3, 5 to 8, and 10 to 14, nor would they be obvious to a person skilled in the art. Neither of documents 1 and 2 discloses an anisotropic conductivity connector characterized in that the elastic polymer material for forming elastic anisotropic conductive films is an addition-curing liquid silicone rubber having a compression permanent set of 10% or less at 150°C and a Shore A durometer hardness of 10 to 60, nor would a person skilled in the art easily conceive of these features.

特許協力条約

REC'L: 0 5 AUG 2004

PCT

特許性に関する国際予備報告 (特許協力条約第二章)

(法第12条、法施行規則第56条) [PCT36条及びPCT規則70]

出願人又は代理人 の書類記号 F-1002	今後の手続きについては、様式	、PCT/IPEA/416を参照すること。			
国際出願番号 PCT/JP03/10056	国際出願日 (日.月.年) 07.08.20	優先日 (日.月.年) 09.08.20	0 2		
国際特許分類 (IPC)	Int. Cl ⁷ H01L21/66				
出願人(氏名又は名称)	JSR株式会社				
囲及び/又は図面の用紙(D規定に従い送付する。 を含めて全部で 3 れている。 ページである。 遊とされた及び/又はこの国際予PCT規則70.16及び実施細則第 したように、出願時における国際	ページからなる。 ページからなる。 	とこの		
配列表に関する補充欄に示すように、コンピュータ読み取り可能な形式による配列表又は配列表に関連するデーブルを含む。(実施細則第802号参照)					
第Ⅳ欄 発明の単一性の	最告の基礎 生又は産業上の利用可能性につい シケ如 2)に規定する新規性、進歩性又に 大及び説明 に献	いての国際予備審査報告の不作成 は産業上の利用可能性についての見解、それ	を裏付		
国際予備審査の請求魯を受理した日 06.02.2004	国際予備領	審査報告を作成した日 15.07.2004			
名称及びあて先 日本国特許庁(IPEA/JP 郵便番号100-8915 東京都千代田区霞が関三丁目4	番3号	在官(権限のある職員) 4R 9 坂本 燕昭 03-3581-1101 内線 636	265		

特許性に関する国際予備報告

国際出願番号 PCT/JP03/10056

第I欄	報告の基礎・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・
1. この	国際予備審査報告は、下記に示す場合を除くほか、国際出願の言語を基礎とした。
	この報告は、
	の報告は下記の出願書類を基礎とした。 (法第6条 (PCT14条) の規定に基づく命令に応答するために提出され 上用紙は、この報告において「出願時」とし、この報告に添付していない。)
	出願時の国際出願書類
×	明細書 ページ、出願時に提出されたもの 第 ページ*、 付けで国際予備審査機関が受理したもの 第 ページ*、 付けで国際予備審査機関が受理したもの
· ×	請求の範囲 項、 出願時に提出されたもの 第 項*、PCT19条の規定に基づき補正されたもの 第 項*、PCT19条の規定に基づき補正されたもの 項*、08.07.2004 付けで国際予備審査機関が受理したもの 項*、付けで国際予備審査機関が受理したもの
×	図面 第 1/12-12/12 ページ /図 、 出願時に提出されたもの 第
	配列表又は関連するテーブル 配列表に関する補充欄を参照すること。
3. 🗵	補正により、下記の書類が削除された。 □ 明細書 第
4.	この報告は、補充欄に示したように、この報告に添付されかつ以下に示した補正が出願時における開示の範囲を超えてされたものと認められるので、その補正がされなかったものとして作成した。 (PCT規則70.2(c)) 明細書 第
* 4.	に該当する場合、その用紙に "superseded" と記入されることがある。

特許性に関する国際予備報告

国際出願番号 PCT/JP03/10056

第V	「棡 新規性、進歩性又は産業上 それを裏付ける文献及び説		についての法第12条 (PCT3	5条(2)) に定める見解、 	
1.	見解				
	新規性(N)	請求の範囲 請求の範囲	1-3, 5-8, 10-14		有 無
	進歩性(IS)	請求の範囲 請求の範囲	1-3, 5-8, 10-14		有 無
	産業上の利用可能性(IA)	請求の範囲 請求の範囲	1-3, 5-8, 10-14		有 無 ·

2. 文献及び説明 (PCT規則70.7)

文献1:WO 02/47149 A1 (ジェイエスアール株式会社) 2:JP 2002-203879 A (ジェイエスアール株式会社)

請求の範囲1-3,5-8,10-14に記載された発明は、国際調査報告に引用されたいずれの文献にも記載されておらず、当業者にとって自明なものでもない。文献1-2には、弾性異方導電膜を形成する弾性高分子物質は、付加型液状シリコーンゴムの硬化物であって、その150℃における圧縮永久歪みが10%以下で、かつ、デュロメーターA硬度が10~60のものである異方導電性コネクターが記載されておらず、しかもその点は当業者といえども容易に想到し得ないものである。

8 5

請 求 の 範 囲

1. (補正後)ウエハに形成された複数の集積回路の各々について、当該集積回路の電気的検査をウエハの状態で行うために、検査用回路基板の表面に配置されて当該検査用回路基板とウエハとを電気的に接続するための異方導電性コネクターにおいて、

検査対象であるウエハに形成された全てのまたは一部の集積回路における被検 査電極が配置された電極領域に対応してそれぞれ厚み方向に伸びる複数の異方導 電膜配置用孔が形成されたフレーム板と、このフレーム板の各異方導電膜配置用 孔内に配置され、当該異方導電膜配置用孔の周辺部に支持された複数の弾性異方 導電膜とよりなり、

前記弾性異方導電膜の各々は、弾性高分子物質により形成され、検査対象であるウエハに形成された集積回路における被検査電極に対応して配置された、磁性を示す導電性粒子が密に含有されてなる厚み方向に伸びる複数の接続用導電部、およびこれらの接続用導電部を相互に絶縁する絶縁部を有する機能部と、この機能部の周縁に一体に形成され、前記フレーム板における異方導電膜配置用孔の周辺部に固定された被支持部とよりなり、

前記弾性異方導電膜における接続用導電部に含有された導電性粒子は、磁性を示す芯粒子の表面に高導電性金属が被覆されてなり、当該芯粒子に対する高導電性金属の割合が15質量%以上であり、かつ、下記式(1)によって算出される、高導電性金属による被覆層の厚みtが50nm以上であり、

前記弾性異方導電膜を形成する弾性高分子物質は、付加型液状シリコーンゴムの硬化物であって、その150 における圧縮永久歪みが10 %以下で、かつ、デュロメーターA硬度が $10\sim60$ のものであることを特徴とする異方導電性コネクター。

式(1) $t = [1/(Sw \cdot \rho)] \times [N/(1-N)]$

〔但し、t は高導電性金属による被覆層の厚み(m)、Swは芯粒子のBET比表面積(m²/kg)、ρは高導電性金属の比重(kg/m³)、Nは(高導電

性金属の質量/導電性粒子全体の質量)の値を示す。〕

2. 導電性粒子は、下記に示す電気抵抗値Rの値が0.3 Ω以下であることを特徴とする請求の範囲第1項に記載の異方導電性コネクター。

電気抵抗値R:導電性粒子0.6gと液状ゴム0.8gとを混練することによってペースト組成物を調製し、このペースト組成物を、0.5mmの離間距離で互いに対向するよう配置された、それぞれ径が1mmの一対の電極間に配置し、この一対の電極間に0.3Tの磁場を作用させ、この状態で当該一対の電極間の電気抵抗値が安定するまで放置したときの当該電気抵抗値。

- 3. 導電性粒子は、BET比表面積が $10\sim500\,\mathrm{m}^2$ / k g であることを特徴とする請求の範囲第1 項または第2 項に記載の異方導電性コネクター。
- 4. (削除)
- 5. (補正後) 弾性異方導電膜を形成する弾性高分子物質は、そのデュロメーターA硬度が25~40のものであることを特徴とする請求の範囲第1項乃至第3項のいずれかに記載の異方導電性コネクター。
- 6. (補正後)弾性異方導電膜を形成する弾性高分子物質は、その引き裂き強度が8kN/m以上のものであることを特徴とする請求の範囲第1項乃至第3項および第5項のいずれかに記載の異方導電性コネクター。
- 7. (補正後)フレーム板の線熱膨張係数が 3×10⁻⁵/K以下であることを特徴とする請求の範囲第1項乃至第3項、第5項および第6項のいずれかに記載の異方導電性コネクター。
- 8. (補正後)請求の範囲第1項乃至第3項および第5項乃至第7項のいずれかに記載の異方導電性コネクターにおける弾性異方導電膜を形成するための導電性ペースト組成物であって、

硬化可能な液状シリコーンゴムと、磁性を示す芯粒子の表面に高導電性金属が被覆されてなる導電性粒子とを含有してなり、前記導電性粒子は、芯粒子に対する高導電性金属の割合が15質量%以上であり、かつ、請求の範囲第1項に記載の数式によって算出される、高導電性金属による被覆層の厚みtが50nm以上であり、

前記液状シリコーンゴムは、その硬化物の150 における圧縮永久歪みが10 %以下で、かつ、デュロメーターA硬度が10 ~ 60 のものであることを特徴とする導電性ペースト組成物。

9. (削除)

10. (補正後) ウエハに形成された複数の集積回路の各々について、当該集積回路の電気的検査をウエハの状態で行うために用いられるプローブ部材であって

検査対象であるウエハに形成された集積回路における被検査電極のパターンに 対応するパターンに従って検査電極が表面に形成された検査用回路基板と、この 検査用回路基板の表面に配置された、請求の範囲第1項乃至第3項および第5項 乃至第7項のいずれかに記載の異方導電性コネクターとを具えてなることを特徴 とするプローブ部材。

- 11. 異方導電性コネクターにおけるフレーム板の線熱膨張係数が 3×10⁻⁵/K以下であり、検査用回路基板を構成する基板材料の線熱膨張係数が 3×10⁻⁵/K以下であることを特徴とする請求の範囲第10項に記載のプローブ部材。
- 12. 異方導電性コネクター上に、絶縁性シートと、この絶縁性シートをその厚み方向に貫通して伸び、被検査電極のパターンに対応するパターンに従って配置された複数の電極構造体とよりなるシート状コネクターが配置されていることを特徴とする請求の範囲第10項または第11項に記載のプローブ部材。
- 13. ウエハに形成された複数の集積回路の各々について、当該集積回路の電気的検査をウエハの状態で行うウエハ検査装置において、

請求の範囲第10項乃至第12項のいずれかに記載のプローブ部材を具えてなり、当該プローブ部材を介して、検査対象であるウエハに形成された集積回路に対する電気的接続が達成されることを特徴とするウエハ検査装置。

14. ウエハに形成された複数の集積回路の各々を、請求の範囲第10項乃至第12項のいずれかに記載のプローブ部材を介してテスターに電気的に接続し、当該ウエハに形成された集積回路の電気的検査を実行することを特徴とするウエハ検査方法。